Fabrication Fe/Fe₃O₄/Graphene Nanocomposite Electrode Material for Rechargeable Ni/Fe Batteries in Hybrid Electric Vehicles

Harish Kumar^{1,*}, A. K. Shukla²

¹Department of Chemistry, Chaudhary Devi Lal University, Sisra - 125 055 (Haryana), India

²Solid State and Structural Chemistry Unit (SSCU), Indian Institute Of Science, Bangalore - 560 012, India

*E-mail address: harimoudgil1@rediffmail.com

ABSTRACT

Fe/Fe₃O₄/Graphene composite electrode material was synthesized by a thermal reduction method and then used as anode material along with Nickel cathode in rechargeable Ni/Fe alkaline batteries in hybrid electric vehicles. Reduced graphene /Fe/Fe₃O₄ composite electrode material was prepared using a facile three step synthesis involving synthesis of iron oxalate and subsequent reduction of exfoliated graphene oxide and iron oxalate by thermal decomposition method. The synthesis approach presents a promising route for a large-scale production of reduced graphene /Fe/Fe₃O₄ composite as electrode material for Ni/Fe rechargeable batteries. The particle size and structure of the samples were characterized by SEM and XRD.

Keywords: Graphene; Nanocomposite; rechargeable batteries; Fe₃O₄

1. INTRODUCTION

As stock of nonrenewable fossil fuel is limited and there is constant demand in shifting towards use of renewable source of energy. Large scale batteries can be used in propulsion of electrical powered vehicles. Safe, low cost, and high energy density are the basic requirements of it. Among the few large scale batteries used in electric vehicle propulsion, of particular interest are lithium ion batteries, in which LiFePO₄ is used as the cathode material, Ni-Cd, metal hydride and Ni/Fe batteries. Lithium ion batteries are limited in safety owing to the flammable organic electrolyte contained inside. In contrast, alkaline rechargeable batteries satisfy safety concerns owing to their use of an aqueous electrolyte. The Ni-Fe rechargeable alkaline battery, in which iron is used as the anode and Ni(OH)₂ as the cathode material, was developed around 1900, and has a cycle life of 3000 cycles and a calendar life of about 20 years [1]. Nickel-iron batteries are highly promising for large scale battery applications owing to their high theoretical capacity [2], inexpensiveness, and absence of toxic materials [3].

Although the theoretical capacity of iron is 962 mAhg⁻¹, but in actual lab test conditions, the iron electrode performed as low as 1/3 of the theoretical value [4-7], owing to the formation of a passive film [8,18]. While attempting to enhance the capacity and power

density of iron active materials, researchers has [9] used the nanosized iron particle, in which the nanosized iron particle discharge capacity is about $700 \text{ mAhg}^{-1}(\text{Fe})$ during the first cycle, a capacity that was significantly higher than in other studies. However, the capacity of the active material decreases quickly to less than 300 mAhg^{-1} during the second or third cycle. Although, other investigators made nanosized iron active materials, the reversibility was not improved [10-14]. This work describes a novel composite structure, Fe/Fe₃O₄/Graphene composite as negative electrode material and Ni hydroxide as a positive electrode for a rechargeable Ni/Fe alkaline batteries with high capacity, large cycle life, high power and energy density.

2. EXPERIMENTAL

2. 1. Preparation of active material i.e. Iron oxalate as precursor

For the synthesis of iron oxalate. 36.2 g of oxalic acid (C₂H₂O₄·2H₂O) of AR grade (S. D. Fine-Chem. limited, Mumbai) was dissolved in double distilled water. Nitrogen gas was passed continuously and solution was heated at 80 °C on hot plate. In another beaker, 73.86 g of FeSO₄·7H₂O ExcelsaR grade (Fisher Scientific Pvt. Ltd., Mumbai) was dissolved in double distilled water. Resulting solution was heated to 80 °C on hot plate with continuous supply of nitrogen gas up to 15 minutes to remove traces of any dissolved gases.

Oxalic acid solution was slowly added in to ferrous sulphate solution with continuous stirring with magnetic stirrer maintained at a constant temperature of 70.0 °C. The mixture was heated with continuous stirring up to 2 hours. Initially, ferrous sulphate solution was brown in colour. On adding oxalic acid, solution becomes greenish in colour. On ageing solution becomes yellowish in colour. Then we filtered it on Whattmann filter paper fitted with suction pump and washed the precipitate (ferrous oxalate) with deionized water several times. Resulting precipitate was dried in oven maintained at 80.0 °C for a period of 4 hours. Then we weighed it and stored it.

2. 2. Preparation of Fe/Fe₃O₄ /Graphene composite for the Negative Electrode

30 mg of exfoliated graphene oxide was added in 50 ml of deionized water in 250 ml capacity glass borosil beaker. Then it was kept for ultrasonication for two hours to completely disperse graphene oxide. Then, we added 6.0 g of iron oxalate into it and again ultrasonicate it for one hour. Then the solution was heated at a temperature of 65-70 °C with continuous stirring till the formation of gel like semisolid paste. Then we put it in an oven to dry for 4 hours maintained at a constant temperature of 80 °C.

Amount of iron oxalate graphene oxide obtained was 5.9 g. Then it was thermally decomposed with the help of tubular furnace fitted with vacuum pump maintained at a pressure of 0.05 mbar initially at 200 °C for 45 minutes and then at 400 °C again for 45 minutes and then at 600 °C again for 45 minutes. Then it was kept in it for slowly cooling. Then it was cooled under liquid nitrogen and then stored in vacuum desiccator. The final product is Fe/Fe₃O₄ /Graphene composite electrode material.

2.3 Preparation of Iron electrode and cell assembly

For the preparation of negative electrode, 1.0 % KOH and 0.0021 m of NiSO₄·7H₂O was taken in 50 ml glass beaker. Then, 1.0000 g of Fe/Fe₃O₄ /Graphene composite was added into it along with 12.4 mg of Bi₂S₃. Then we weighed 0.1346 g of PTFE in another 50 ml

beaker and added few drops of water into it to dilute it. Then we mix the two to form paste like gel. Then this paste was applied uniformly on both sides of nickel coated iron mesh and put under a load of 65.5 kilo newton for 5.0 minutes. Then the electrode was placed between glass watch slides and put in tubular glass frame through which continuous supply of N₂ gas was maintained at a rate of one bubble per two seconds. After 15 minutes, tubular glass frame having working electrode was placed in muffle furnace maintained at 350 °C for minutes with continuous supply of nitrogen gas.

For making the cell, we assembled counter electrode i.e. Ni(OH)₂ supported over stainless steel wire gauze available commercially acting as positive electrode, working test electrode of Fe/ Fe₃O₄ /Graphene acting as negative electrode and a reference electrode i.e. Hg/Hg₂Cl₂ fitted with luggin capillary in the centre of PVC plastic container beaker of approx. 270 ml capacity. Electrolyte used was 6.0 m KOH and 1.0 wt. % of LiOH.

3. RESULT AND DISCUSSION

3. 1. Electrochemical characterization of Working Electrode

For the electrochemical characterization of working electrode, we assembled it on multichannel electrochemical workstation (Autolab) for charging-discharge cycle rate and electrochemical impedance study. Figure 1 shows XRD pattern of Fe/ Fe₃O₄ /Graphene (35 mg) negative electrode material. The peak at an angle of 30.218° (220), 35.612° (311), 43.278° (400), 53.569° (422), 57.118° (511), 62.655° (440) correspond to Fe₃O₄. Two peak corresponding to 44.768° (110) and 65.139° (200) confirms the presence of metallic Fe. A peak 18.364° corresponds to the graphene.

Figure 2 shows XRD pattern of Fe/ Fe₃O₄ Graphene (45 mg) negative electrode material. The peak at an angle of 30.218° (220), 35.612° (311), 43.278° (400), 53.569° (422), 57.118° (511), 62.655° (440) correspond to Fe₃O₄. Two peak corresponding to 44.768° (110) and 65.139° (200) confirms the presence of metallic Fe. A peak 18.364° corresponds to the graphene.

Figure 3 shows capacity evolution during the first 25 cycles of charge-discharge of Fe/ Fe₃O₄ /Graphene (30 mg) negative electrode. After some stabilization cycles, which are necessary for the distribution of the sulphate ions in the Fe electrode surface, the electrode shows a marked increase in capacity from 191.01 to 277 mAh/g. The charging current was 62.5 mA for 8 hours and discharging current was 50 mA/g. The nominal (operating or discharge) voltage of Ni/Fe cells could vary from about 1.23 V at the C/8 rate to 0.85 V at the C rate.

The charge-discharge reactions of the Ni/Fe battery are

Figure 1. XRD pattern of Fe/ Fe_3O_4 Graphene (30 mg) negative electrode material.

Figure 4 shows capacity evolution during the first 25 cycles of charge/discharge of Fe/ Fe_3O_4 /Graphene (45 mg) negative electrode. The results are almost similar to previous electrode. Figure 5 shows impedance study of Fe/ Fe_3O_4 /Graphene (30 mg) electrode (Nyquist plot). Figure 6 shows impedance study of Fe/ Fe_3O_4 /Graphene (45 mg) electrode (Nyquist plot). Electrochemical impedance spectroscopy (EIS) experiments were performed at constant Potential (AC amplitude/RMS voltage), using a 5.0 mV peak to peak ac potential perturbation in discharge condition at OCP value of -0.93 V versus Hg/HgO in frequency range 100 kHz to 5 mHz. At each selected potential, the EIS measurement was performed only when a steady state dc current had become established. Impedance spectra, recorded at constant potential for a Fe/ Fe_3O_4 Graphene electrode in 6.0 M KOH solution are presented in the Nyquist (complex plane) representation in Fig. 6. Before recording each spectrum, the electrode was first kept at the applied potential to equilibrate for 300 s. The corresponding Naquist plot can be as Figure 5 and 6 and we can confirm that the impedance curve with respect to frequency is a hyperbola suggesting porous pore electrode due to adsorption of graphene molecules on Fe_3O_4 electrodes [15].

Scanning electron microscopy (SEM) was performed to investigate structure, morphology and size of electrode material before discharge-charge cycles measurement. Figure 7 shows SEM images of Fe/ Fe_3O_4 /Graphene electrode material synthesized by above procedure taken from JEOL JSM 5600LV make SEM instrument. XRD and SEM results shows that the Fe_3O_4 that is produced through oxidation of iron oxalate is reduced to Fe through $\text{Fe}(\text{OH})_2$ [16].

Figure 2. XRD pattern of Fe/ Fe_3O_4 /Graphene (45 mg) negative electrode material.

Figure 3. Capacity values of Fe/ Fe₃O₄ /Graphene (30 mg) negative electrode as a function of charge/discharge cycle.

Figure 4. Capacity values of Fe/ Fe₃O₄ /Graphene (45 mg) negative electrode as a function of charge/discharge cycle.

Figure 5. Impedance study of Fe/Fe₃O₄/Graphene electrode (Nyquist Plot).

Figure 6. Impedance study of Fe/Fe₃O₄/Graphene electrode (Nyquist Plot).

a) SEM image at X1,000 magnification.

b) SEM image at X2,500 magnification.

c) SEM image at X5,000 magnification.

d) SEM image at X10,000 magnification.

Figure 7. SEM images of Fe/ Fe₃O₄ /Graphene negative electrode material.

Therefore, it is likely that the uniform dispersion of Fe particles is attributable to the dissolution-deposition process between Fe and $\text{Fe}(\text{OH})_2$ via HFeO_2^- [17].

SEM micrographs of the magnetite powders demonstrate that the morphology of the oxalate crystals is preserved during the course of thermal decomposition and has a strong impact on the shape and agglomeration behavior of the magnetite particles. The β -oxalate crystals have transformed into magnetite at 400 and 600 °C under grain growth conditions of 45 minutes. The obtained magnetite consists of bulky agglomerates of 2-3 μm size (Fig. 7c) that do hardly form bigger agglomerates. Magnetite prepared at 600 °C still consists of loose agglomerates. In contrast, thermal decomposition transforms the larger prism-shaped α -ferrous-oxalate crystals into completely different magnetite morphology.

4. CONCLUSIONS

Fe/Fe₃O₄/Graphene composite electrode material was synthesized by a thermal reduction method and then used as anode material for a rechargeable Ni/Fe alkaline batteries. Reduced graphene /Fe/Fe₃O₄ composite electrode material was prepared using a facile three step synthesis involving synthesis of iron oxalate and subsequent reduction of exfoliated graphene oxide and iron oxalate by thermal decomposition method. The synthesis approach presents a promising route for a large-scale production of reduced graphene /Fe/Fe₃O₄ composite as electrode material for Ni/Fe rechargeable batteries. The particle size and structure of the samples were characterized by SEM and XRD. Their electrochemical performance was also studied. Internal resistance found from impedance study was 50 and 51 mohm for Fe/Fe₃O₄ /Graphene 1 and 2 electrodes, respectively. As an anode material for Ni/Fe batteries, reduced graphene /Fe/Fe₃O₄ composite exhibited discharge and charge capacities of 280 mAh/g, based on total mass of composite, with good cycling performance and rate capability. The result shows that the Fe/Fe₃O₄ /Graphene composite electrode material prepared by this method is nanosized.

References

- [1] A. K. Shukla, S. Venugopalan, B. Hariprakash, *J. Power Sources* 100 (2001) 125.
- [2] P. Periasamy, B. R. Babu, S. V. Iyer, *J. Power Sources* 62 (1996) 9.
- [3] C. A. C. Souza, I.A. Carlos, M. Lopes, G.A. Finazzi, M. R. H. de Almeida, *J. Power Sources* 132 (2004) 288.
- [4] D. Yamashita, Y. Yamamoto, K. Masuse, H. Yoshida, *Nippon Kagaku Kaishi* (1978) 525.
- [5] C. Chakkaravarthy, P. Periasamy, S. Jegannathan, K. I. Vasu, *J. Power Sources* 35 (1991) 21.
- [6] A. K. Shukla, M. K. Ravikumar, T. S. Balasubramanian, *J. Power Sources* 51 (1994) 29.
- [7] M. K. Ravikumar, T. S. Balasubramanian, A. K. Shukla, *J. Power Sources* 56 (1995) 209.
- [8] W. C. He, H. B. Shao, Q. Q. Chen, J. M. Wang, J. Q. Mang, *Acta Phys. Chim. Sin.* 23 (2007) 1525.

-
- [9] K. C. Huang, K. S. Chou, *Electrochem. Commun.* 9 (2007) 1907.
- [10] B. T. Hang, M. Eashira, I. Watanabe, S. Okada, J. I. Yamaki, S. H. Yoon, I. Mochida, *J. Power Sources* 143 (2005) 256.
- [11] B. T. Hang, H. Hayashi, S. H. Yoon, S. Okada, J. Yamaki, *J. Power Sources* 178 (2008) 393.
- [12] B. T. Hang, T. Watanabe, M. Eashira, S. Okada, J. Yamaki, S. Hata, S. H. Yoon, I. Mochida, *J. Power Sources* 150 (2005) 261.
- [13] B. T. Hang, T. Watanabe, M. Eashira, I. Watanabe, S. Okada, J. Yamaki, *Electrochem. Solid State Lett.* 8 (2005) A 476.
- [14] K. Ujimine, A. Tsutsumi, *J. Power Sources* 160 (2006) 1431.
- [15] Chen-Yu Kao, Kan-Sen Chou, *J. Power Sources* 195 (2010) 2399-2404.
- [16] Kuo-Cheng Huang, Kan-Sen Chou, *Electrochemistry Communications* 9 (2007) 1907-1912.
- [17] A. K. Shukla, S. Venugopalan, B. Hariprakash, *J. Power Sources* 100 (2001) 125-148.
- [18] W. Sienicki, M. Wojtewicz, *International Letters of Chemistry, Physics and Astronomy* 4 (2012) 76-81.

(Received 11 September 2013; accepted 15 September 2013)