The self ignition of fiberglass lines

Moussa Bounoughaz^{1, 2,*}, Noura Touabi^{1,2}

¹Département de Chimie, Faculté des Sciences, Université M'hamed Bougara, Boumerdès, Algeria

²Laboratoire Traitement et Mise en Forme des Polymères Fibreux, Département Génie des Procédés, Faculté Sciences de l'Ingénieurs, Boumerdes Université M'hamed Bougara, Boumerdès, Algeria

*E-mail address: moussa_bounoughaz@yahoo.fr

ABSTRACT

The fiberglass pipes were used for transportation of water in order to maintain the pressure in the oil field of Zarzaitine (Region of In Amenas located in the south of Algeria). During the maintenance work in summer, a season well known for its extensive heat, the deposits contained in the pipe, and after its contact with the atmosphere, have caused a smoke and it was followed by a fire that ignited a portion of the pipe. To give an answer to the causes of this phenomenon, we have first incriminated the role of specific bacterial species and therefore we have made a microbiological analysis of the deposits collected from the site of the incident. The obtained results revealed the presence of a heterogeneous microbial population with a high concentration level of sulfate-reducing bacteria (SRB), methanogenic bacteria (MB), yeasts and fungi. The interaction between the different species of bacteria and the organic matter contained in the deposits has generated the formation of methane which under the influence of the great heat burnt and the fire caused the ignition of the fiberglass line.

Keywords: Self-ignition; deposits; fiberglass; aerobic bacteria; facultative anaerobic; sulfate-reducing bacteria; methanogenic bacteria

1. INTRODUCTION

Zarzaitine oil field located in the south of Algeria was known for the self ignition that it was produced in the fiberglass lines that were transformed into embers a few hours after its opening for maintenance. These lines were used to collect water from wells. These waters produced by gas lift process were treated by additives like biocides, corrosion inhibitors and oxygen scavengers. Biocides and corrosion inhibitors were injected in the bottom of wells. Incompatible additives form an organic scale that precipitate in the bottom of lines. With the presence of bacteria, the organic phase of scale may be altered and thus forms several products like methane (CH₄), sulfur acid (H₂S), carbon dioxide (CO₂) and oxygen (O₂). At the same time, operators in charge of maintenance of the unit of Closing Gas Lift (CGL) have noticed the increase in temperature of the deposits removed from capacities and separators of CGL unit. These deposits where transformed into embers. All these phenomena occurred during the month of July when the temperature is usually very high. Deposits, after their contact with the atmosphere, produced a smoke and turned into a brazier causing the auto inflammation of fiberglass pipes.

According to researchers [1] sulfate reduction may cause several problems in the anaerobic treatment process and have been studied regarding the following points:

- (a) sulfate is reduced to hydrogen sulfide which is a strong inhibitor of methanogenesis bacteria;
- (b) sulfide has a piquant odor and exerts a high oxygen demand in the effluent;
- (c) hydrogen sulfide released to the biogas causes corrosion downstream;
- (d) sulfate reducing bacteria (SRB) competes with other bacteria associated with methane production. The methanogenesis as the terminal step of anaerobic degradation yields to a competition between SRB and methane producing bacteria (MPB).

As reported by researchers [2], sulfate reduces to H_2S and oxidizes organic matter to produce CO_2 and the alkalization of medium in anaerobic process. The organic matter breaks down into CH_4 and CO_2 and it can be expressed as follow:

The temperature of the auto ignition is the minimum temperature in which a material must be heated to initiate combustion without the need of external flame [3,4]. Fei et al propose the mechanism for self ignition and they suggest that the heat generated by exothermic reaction will not dissipate in time. The combustion occurs at the place where oxygen exists. The sequences of self ignition go as follows:

First, the material must exhibit self heating.

Second, self heating must reach a critical high temperature rapidly.

Third, a sustained smoldering starts.

Fourth, the sustained smoldering reaches the outside of the material then erupts into flaming.

The spontaneous ignition is an uncontrolled and undesirable action and may lead to serious damages in many areas of the economical and industrial sectors [5]. The same results were observed within the scales founded into the down areas of the capacities of CGL unit in In Amenas oilfields.

Spontaneous ignition was observed regularly in coal mines and storage facilities and piles of plastic, dust, and tires. Auto ignition temperature (AIT) was identified as the temperature at which no heat transfer occurred between the surface and the center of the sample and in some other studies AIT was the temperature at which the sample temperature equaled the temperature of the furnace. The crossing-point method was adopted in this study to determine the AIT for various components of solid waste, determined as the point of equal temperature between the surface and the center of the sample [6]. Moisture can generally promote chemical self-heating and the heat generated from chemical oxidation plays a major role in spontaneous combustion.

As reported by authors [7-8], fresh organic waste is sensitive to oxidation by biodegradation and presents a higher risk for spontaneous combustion. The biodegradation is accelerated by the intense activity of bacteria. The presence of carbon monoxide (CO) gas gives a good indication for imminent self ignition

A biological reaction that causes the self-heating of organic agricultural products is usually the oxidation assisted by microorganisms in the presence of water. Other chemical compounds, mainly inorganic, react with water to produce heat and can cause spontaneous ignition. Materials that react with water are not combustible themselves, but they produce sufficient heat to ignite nearby combustibles or flammable gases produced by the reaction [9].

The injected water is characterized by the presence of high concentration in sulfates, Sulfate Reducing Bacteria (SRB), and sufficient biodegradable organic materials and nutrients. In the absence of oxygen, the metabolism and the growth of SRB produces hydrogen sulfide (H_2S) [10].

Methane (CH_4) is stable in anaerobic environments. It poses a distinct explosion hazard when it is in the range of 5.53-14 % (v/v) in the presence of oxygen. Methane concentration in the explosive range is of particular concern in the confined space of underground mining environments where the hazards of accidental ignition of methane may be further compounded by coal dust explosions [11].

In the same order, Albert et al [12] mentioned that the accumulation of hydrogen sulfide in sewer systems is a well known problem resulting in sewer wall corrosion, serious health hazards and odor. Hydrogen sulfide (H_2S) is formed when the organic matter present in sewage is oxidized under sulfate-reducing anaerobic conditions. However, hydrogen sulfide is not the unique compound formed from the sewer systems.

2. MATERIALS AND METHODS

Four scale samples were collected from different levels of the filtration battery located in the head of the well used for injecting water. Sediments were identified as follow: dry sediment (DS), humid sediment (HS), sediment of surface (SS) and sediment from the depth of filters (SD). All the samples were introduced into sterile plastic bags.

Samples from injection water and water formation have been collected at the head of injecting well water and from head of oil well respectively. All The samples were filled with overflow in sterile glass bottles to prevent their contact with air and then sealed with rubber stoppers. Scales and water samples were transported by ice box and were analyzed within two days. Table 1 presents the chemical composition of the injection and formation water samples collected at Zarzaitine oil field.

Table 1. Chemical composition of the injection and formation waters.

Elements (mg/l)	Injection water	Formation water
Na^+	6600	30250
K	120	655
Ca^{2+}	1026.0	11735.4
Mg^{2+}	311.3	1303.6
Sr^{2+}	20	230
Ba^+	0	1600.2
Fe^{2+}	0	20.03
Cl^-	9474.1	74176
CO_3^{2-}	0	0
HCO_3^-	275.7	72

SO ₄ ²⁻	3646.1	0
pH	7.30	6.06
Hydrocarbon	1.23	30.20
Suspended matters (filtered at 0.45 µm)	112	496

2. 1. Culture of bacteria

Water injection was filtered, sterilized and used in the preparation of the medium of culture for SRB and MG. The medium used for enrichment and growth of SRB in the anaerobic conditions is formed by (in g/l): 0.5 KH₂PO₄, 1.0 NH₄SO₄, 1.0 Na₂SO₄, 1.0 CaCl₂ 6H₂O, 2.0 MgCl₂ 7H₂O, 3.5 sodium lactate, 0.5 yeast extract, 0.1 ascorbic acid, 0.1 thioglycolic acid, 0.5 FeSO₄ 7H₂O and 1.5 agar.

The pH of the media was adjusted to 7.6 with NaOH [13]. The dissolution was carried out by adding sterile water injection to maintain the same physiological concentration that yields to optimal conditions for bacterial growth. The chemical composition of this water is given in table 1. In each bottle, an iron nail of 6 mm was added to the medium. Medium culture was dispensed into penicillin bottles and made anaerobic by bubbling N₂-CO₂ in the range of 80:20 v/v respectively.

The filled bottles were sealed with rubber stoppers and aluminum caps and then purged with mixed gas (N₂:CO). The series of bottles were autoclaved and kept for later use. The medium of culture for yeast fungi was made from yeast (10 g/l), malt extract (7 g/l) and dextrose agar (20 g/l) [14].

The inoculums were prepared by dissolving 2 g of each samples in 250 ml sterile flasks and filled with mediums as prepared previously. The flasks were introduced in adjustable incubators as shown in Table 2. The inoculums were serving as sources of high contamination by different germs to be used for counting, analysis and examinations.

Table 2. Inoculums incubator conditions.

Conditions Boîtes pour bactéries	Temperature Of incubation	Aerobic /Anaerobic conditions
Total germs	37 °C	Aerobic
Yeast fongi	37 °C	Aerobic
SRB	37 °C	Anaerobic
Methanogenic	32 °C	Anaerobic
Methanogenic	37 °C	Anaerobic

Methanogenic enrichment culture used for detecting and characterizing a methanogenic bacteria present in solutions was prepared from previous sediment samples. Liquid samples were transferred to a nutrient medium containing standard methanogenic substrates. The

culture solutions filled into sterile vials were also sealed with rubber stoppers and aluminum caps, purged with mixed gas ($N_2:CO_2 = 8:2$) and incubated at 32 °C for 48 hours. Culture growth and production of methane serves as a positive indication of the presence of methanogenic bacteria. The culture medium used for the SRB growth was adapted for the methanogenic bacteria by adding supplemental trace elements, protein and enzymes [15]. Agar was added to promote colonies growth on Petri boxes.

For enumerating SRB, 1ml of SRB inoculums was injected into penicillin bottle containing 9 ml of specific medium for SRB. The bottle was shaken thoroughly, and the new sterile syringe was used to draw out 1 ml sample and injected into a new medium bottle. This procedure was repeated to produce a serial of 6-8 bottles. The concentrations of inoculums in the bottles were $1 \cdot 10^0$, $1 \cdot 10^{-1}$, $1 \cdot 10^{-2}$ and $1 \cdot 10^{-n}$, where n is the last bottle in the serial. The anaerobic bottles were then incubated at 37 °C and monitored daily for blackening due to FeS formation for up to 28 days [16].

3. RESULTS AND DISCUSSION

3. 1. Sulfate reducing bacteria (SRB)

For SRB, enrichment cultures were incubated at 37 °C during 28 days. Growth was regarded as positive based on visual observation of the blackening of the medium of culture. The growth of SRB forms sulfur acid (H_2S) that reacts with iron nail to form black scale of iron sulfide (FeS). The microbiological characteristics of SRB were shown in table 3. All samples are highly contaminated by SRB ($> 10^5$ germs/ml). The diameter of cells is less than 1 mm, with the exception of the SD sample where the diameter of SRB bacteria was equal 1 mm.

Cells were mobile and the microscopic examination revealed a Gram-negative for HS and SS samples and Gram positive for DS et SD samples. Three principal shapes of bacteria were observed: spherical (coccus), rod (bacillus) and twisted rod (spirillum). The coccus may be arranged in chains of cocci as in *streptococcus*, or in tetrads of cocci as in *Sarcina*. The diameter of SRB is less or equal than 1 mm, which facilitates their accumulation in the battery of filtration since this latter has a smaller diameter that is equal to 0.45 microns.

The results shown in Table 3 revealed the presence of complex bacterial and archaeal communities that were involved in the reduction of sulfur-containing compounds (sulfate, thiosulfate, elemental sulfur) to sulfide. Thiosulfate, sulfur and sulfate-reducing bacteria have been commonly isolated from oil field and water production-injection systems.

A few decades ago, more attention was given to SRB regarding their influence on corrosion of metallic installations that causes economical losses for companies. SRB corrosion is one of the main factors causing the degradation of pipeline in oilfields. SRB tends to form a biofilm near the cathodic area.

The colonies located on the surface walls of separators and pipelines increase the rate of corrosion and lead to the pollution of soils and atmosphere by leaking considerable amounts of hydrocarbon (oil and condensate). Sulfate-reducing bacteria (SRB) contribute to souring as well as the production of sulfide in oil and gas fields.

H_2S gas is corrosive and toxic and as shown previously causes reservoir plugging. SRB reduces sulfate ions to sulfide ions (S^{2-}) that react with anodic iron ions and form iron sulfide (FeS) that is deposited as corrosion products. The principle reactions explaining bacterial corrosion as reported by authors [17-18] are given by the following equations:

Ionization of water:

Cathodic depolarization:

Corrosion products:

The overall reaction of corrosion:

Corrosion of carbon steel is accelerated by the metabolite of SRB and by the depolarization of cathodic areas containing high concentration of Hydrogen.

SRB growth on metal surfaces changes the properties of the electrical interface. Important changes in the type and concentration of ions, pH values, and oxidation-reduction potential are induced by the biofilm.

Microorganisms influence corrosion rate by changing the electrochemical conditions at the metal-solution interface. These changes may have different effects including the induction of localized corrosion [19].

Table 3. Characterization of SRB found in the four sediments.

Samples	Dry sediment	Humid sediment	Surface sediment	Deep sediment
Number	$> 10^5$ g/ml	$> 10^5$ g/ml	$> 10^5$ g/ml	$> 10^5$ g/ml
Form	Filamentous	Circular	circular	Circular with irregular edge
Diameter	< 1 mm	< 1 mm	< 1 mm	1 mm
Color	whitish	whitish	white	white
Opacity	opaque	opaque	opaque	opaque
elevation	plate	plate	plate	plate
Surface	rough	rough	rough	rough
Consistency	strong	strong	strong	strong
Mobility	mobile	mobile	mobile	mobile
Morphology and Gram	Cocci G^+	bacillus G^-	Coccobacillus G^-	coccobacillus G^+

3. 2. Methanogenic bacteria

The results of microbiological analysis of the methanogenic bacteria are presented in tables 4 and 5. At the temperature of 37 °C and after 5 weeks of incubation, the growth of methanogenic bacteria was negligible in the four samples of deposits.

However, at an incubation temperature of 32 °C, an appreciable population of the methanogenic bacteria was noticed in the four samples of deposits. Many authors have shown in their research that some methanogenic bacteria have an optimal growth between 25 and 30 °C. Microbial methanogenesis is common in nature and is normally associated with the decomposition of organic matter [20-21]. The number of methanogenic bacteria was 10^3 germs/ml in the dry and humid deposit and in the deposit sample collected in the depth of filter. 10^2 germs/ml were found in the deposit collected from the surface of the filter. The dry and the humid deposits have a single type of methanogenic bacteria, while methanogenic bacteria isolated at the filter cartridge shown two different genres of bacteria.

The majority of bacteria were cocci and Gram positive (83.3 %) and 16.6 % of bacteria were coccobacillus and Gram negative. All the methanogenic bacteria were immobile and the macroscopic characteristics differ from one type to another. The culture of methanogenic bacteria was obtained after four weeks of incubation at 32 °C.

Table 4. Characterization of methanogenic bacteria at 32 °C.

Sample	Dry sediment (DS)	Humid sediment (HD)
Counting	10^3 g/ml	10^3 g/ml
Form	circular	filamentous
Diameter	< 1 mm	> 1 mm
Color	White with black center	white
Opacity	opaque	opaque
Elevation	convex	convex
Surface	dry	dry
Consistency	plate	plate
Mobility	Immobile	Immobile
Morphology	Cocci	Cocci
Gram	G ⁺	G ⁺

Table 4(continued). Characterization of methanogenic bacteria at 32 °C.

Sample	Surface filter		Deep filter	
Counting	10^3 germs/ml		10^2 germs/ml	
Form	Circular	irregular	circular	circular
Diameter	< 1 mm	> 1 mm	< 1 mm	> 1 mm
Color	white (black center)	green	white	White(black center)
Opacity	opaque	opaque	opaque	translucide

Elevation	convex	convex	convex	convex
Surface	dry	blunted	dry	rough
Consistency	plate	plate	plate	viscous
Mobility	mobile	immobile	immobile	mobile
Morphology	Cocci	Coccobacille	Cocci	Cocci
Gram	G ⁺	G ⁻	G ⁺	G ⁺

4. CONCLUSIONS

Microbiological analyses performed on deposits collected from the water injector wells, have revealed the presence of a large microbial population. These analyses also reveal a diverse nature of isolated organisms. The filter was more contaminated with bacteria than dry and wet deposits. The morphology of these bacteria is most often type Gram positive and cocci forms. The ability of bacteria to degrade organic products is a well-known phenomenon. The medium contains a mixture of SRB, MB and other cells. Their metabolism products were methane gas, hydrogen sulfur, mono oxide of carbon and several other compounds. The final products associated with the intense solar radiation of summer facilitated the self ignition that lead to burn the fiberglass line.

References

- [1] Vossoughi M., Shakeri M., Alemzadeh I., *Chemical Engineering and Processing* 42 (2003) 811-816.
- [2] Euiso C., Jay R., *Water Sciences Technology* 23 (1991) 1259-1264.
- [3] Tatyana D., Nicholas P. 2011. Fire and explosion hazards handbook of industrial chemicals. Cheremisinoff: p. 223, August 13th.
- [4] Fei F., Liang D., *Procedia Engineering* 11 (2011) 91-99.
- [5] Proce W. H., Marcia M. 2007. Edings of the International Conference on Sustainable Solid Waste Management, 5 - 7 September, Chennai, India, pp. 189-196.
- [6] Shadi M., Debra R., Ruey-Hung C., *Waste Management* 30 (2010) 1600-1607.
- [7] William H., Marcia M., *Conservation and Recycling* 40 (2003) 53-69.
- [8] Torrenta J. G., Á. Ramírez G., Querol-Aragóna E., Grima-Olmedoa C., Medic-Pejica L., Determination of the the risk of self-ignition of coals and biomass materials. *Journal of Hazardous Materials* (2012) Paper in press.
- [9] Tsuchiya Y., Sumi K. (1976). Spontaneous ignition: relation between ambient temperature and size of specimen. National Research Council of Canada.
- [10] Franzmann, P. N., Skyring, G. W., Burton, H. R. and Deprez, P. P., *Hydrobiology* 165 (1985) 25-33.
- [11] Chris A. P., Johannes M. S., Elijah M.T., Karl-Heinz J. R., *Fuel* 82 (2003) 1359-1365.
- [12] Albert G., Keshab R. S., Jurg K., Zhiguo Y., *Water Research* 43(2009) 2874-2884.

-
- [13] Katy J., Susan A., Baldwin M., *Water Resources* 34(3) (2000) 797-806.
 - [14] Ramaraj B., *Bioresource Technology* 55 (1996) 231-235.
 - [15] Friedrich W., *Applied and Environmental Microbiology* 55(5) (1986) 1056-1062.
 - [16] Devender K. Jain, *Journal of Microbiological Methods* 22 (1995) 27-38.
 - [17] Zhang C., Wena F., Cao Y., *Procedia Environmental Sciences* 10 (2011) 1177-1182.
 - [18] Sherar B.W.A., Power I.M., Keech P.G., Mitlin S., Southam G., Shoesmith D.W. *Corrosion Science* 53 (2011) 955-960.
 - [19] Héctor A. Videla, Liz K. Herrera, *International Microbiology* 8 (2005) 169-180.
 - [20] Martina M., Peter F., *Applied and Environmental Microbiology* (2005) 8191-8200.
 - [21] Zaikus J. G., Winfrey M. R., *Applied and Environmental Microbiology* 31(1) (1976) 99-107.

(Received 01 September 2014; accepted 10 September 2014)